

SECTION 892 OIL FOR TREATMENT OF CONCRETE SURFACES

892.1 REQUIREMENTS

If the treating oil is mixed by volume, it shall consist of 50 percent boiled linseed oil conforming to ASTM D 260 and 50 percent kerosene or mineral spirits. If the treating oil is mixed by weight, it shall consist of not less than 54 percent boiled linseed oil.