

SECTION 930 CHAIN LINK FENCE

930.1 REQUIREMENTS

Chain link fence material shall conform to AASHTO M 181. Chain link fabric, posts, rails, ties, bands, bars, rods, and other fittings and hardware shall be Type 1. Posts, rail, and gate frames shall be grade 1 or 2. Grade 2 posts, if used, shall have an exterior PVC coating conforming to class A or an exterior coating of hot-dip zinc plus an organic topcoat and a zinc rich or hot-dip zinc interior coating. The fabric shall have a class C coating. Tension wire shall be class 2.

SECTION 950 WOOD PRESERVATIVES AND PRESERVATIVE TREATMENTS

950.1 REQUIREMENTS

Piling shall be treated with creosote, copper naphthenate, or pentachlorophenol. Round posts, sawed posts, and lumber in contact with the ground shall be treated with ammoniacal copper zinc arsenate, creosote, copper naphthenate, pentachlorophenol, or chromated copper arsenate. Lumber not in contact with the ground shall be treated with ammoniacal copper zinc arsenate, pentachlorophenol, copper naphthenate, or chromated copper arsenate. The preservative treatment shall be in accordance with AWWA Standards as referenced in AASHTO M133.