

SELECT GRANULAR BACKFILL

850.1 REQUIREMENTS

This material shall be free from dirt, vegetation, or other foreign substance. The material shall meet the following gradation requirements by dry weight:

Percent Passing a 1½ inch (37.5 mm) sieve.....	100
Percent Passing a 1 inch (25.0 mm) sieve.....	95-100
Percent Passing a ½ inch (12.5 mm) sieve.....	25-80
Percent Passing a No. 4 (4.74 mm) sieve.....	0-20
Percent Passing a No. 8 (2.36 mm) sieve.....	0-5

Abrasion loss shall not exceed 40 percent.

Sampling and Testing:

Sampling.....	SD 201
Gradation.....	SD 202
LA Abrasion.....	AASHTO T 96