

950.1 REQUIREMENTS

Piling shall be treated with creosote, copper naphthenate, or pentachlorophenol. Round posts, sawed posts, and lumber in contact with the ground shall be treated with ammoniacal copper zinc arsenate, creosote, copper naphthenate, pentachlorophenol, or chromated copper arsenate. Lumber not in contact with the ground shall be treated with ammoniacal copper zinc arsenate, pentachlorophenol, copper naphthenate, or chromated copper arsenate. The preservative treatment shall be in accordance with AWPA Standards as referenced in AASHTO M133. Wood preservative treatment for Western Red Cedar is not required and shall be exempt from the above requirements.